



PATENT ABSTRACTS OF JAPAN

(11)Publication number:

09-245818

(43) Date of publication of application: 19.09.1997

(51)Int.CI.

H01M 8/02 B01D 71/68 C08G 75/23 C08J 5/22 H01M 8/10

(21)Application number : 08-069448

(71)Applicant: AISIN AW CO LTD

AQUEOUS RES:KK

(22)Date of filing:

29.02.1996

(72)Inventor: AZUMA RYUJI


NAGAI KENJI KONDO MASAKO MURASE KAZUHISA

TAKADA CHIKAYUKI

(54) ELECTROLYTE FILM FOR FUEL CELL AND MANUFACTURE THEREOF

(57)Abstract:

PROBLEM TO BE SOLVED: To provide an electrolyte film with higher ion exchange capacity than Nafion and high mechanical strength in spite of higher ion exchange capacity than sulfonated polysulfone, and provide the manufacturing method thereof. SOLUTION: An aromatic ring of polysulfone having a repeating unit represented by the formula is sulfonated to introduce a sulfonic acid group into the aromatic ring, and a sulfonated polysulfone solution having an ion exchange capacity from more than 1.6 milliequivalent/g resin to 3.2 milliequivalent/g resin is obtained as a film forming solution, and the stulfonated polysulfone solution obtained is applied to a substrate to form a coating film, then the coating film is heated at 40–80°C for 12 hours or longer to obtain an electrolyte film. The electrolyte film for a fuel cell has high ion exchange capacity mentioned above, and high mechanical strength of a fitting load pressure of 80kgf/cm2 or higher, and high molding capability.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office